

EUCAFLUFF TECHNICAL DATA SHEET



Typical Properties¹

	Nominal Value	Tolerance	Standard
Basis Weight (g/m ²)	720	± 45	ISO 536
Moisture (%)	7.5	± 1.5	TAPPI 412
Caliper (mm)	0.93	≥ 0.9	ISO 534
Density (g/cm ³)	0.7	± 0.1	ISO 534
Mullen (kPa)	700	≥ 500	ISO 2758
Brightness ISO (%)	89	≥ 87	ISO 2470
Dirt (ppm)	0	≤ 4	TAPPI 437
Average Fiber Length Weighted (mm)	0.8	± 0.2	TAPPI 271
Fiberization (%)	91	≥ 86	MTS method

OBSERVATIONS

(1) Test climate conditions: 23°C / 50% RG (according to ISO 187). Tolerances: based upon 95% confidence limits, applied to reel average. In order to verify, reel average shall be based on 5 single measurements randomly sampled within the reel.

Roll Dimensions

	Nominal Value	Tolerance	
Diameter (mm)	1200	± 200	Different dimensions available upon demand.
Width (mm)	480	± 5	
Core	3"		