

Technical data sheet

Eucafluff® Grades

	Suzano Mill	Limeira Mill	Method
Basis Weight (g/m ²)	720 (± 40)	850 (± 50)	ISO 536
Moisture (%)	7.5 (± 1.5)	7.5 (± 1.5)	TAPPI 412
Mullen (kPa)	650 (≥ 500)	650 (≥ 500)	ISO 2758
Caliper (µm)	930 (≥ 900)	1000 (≥ 1000)	ISO 534
Density (g/cm ³)	0.7 (± 0.1)	0.7 (± 0.1)	ISO 534
Brightness ISO (%)	88 (≥ 87)	88 (≥ 87)	ISO 2470
Dirt (ppm)	0 (≤ 4)	0 (≤ 4)	TAPPI 437
Average Fiber Length Weighted (mm)	0.7 (± 0.2)	0.7 (± 0.2)	ISO 16065-2
Fiberization (%)	93 (≥ 91)	93 (≥ 91)	MTS method
Absorption time (s/g)	1.3 (≤ 1.6)	1.3 (≤ 1.6)	SCAN 33:80
Absorption Capacity (g/g)	8.0 (≥ 6.7)	8.0 (≥ 6.7)	SACN 33:80

Standard available formats

	Nominal Value	Tolerance
Diameter (mm)	1200 or 1500	± 100
Width (mm)	250 or 480	± 3
Core*	3"	

*Recycled cardboard coiled cover with FDA-approved virgin fiber paper.

